

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Withdrawn) A process used to obtain cellulosic wet sheet comprising:
 - a) heating a solution containing 0.2 to 12% of glucose mass and 0.1 to 7% of yeast extract in water that was filtered through sand and activated charcoal in a sanitary stainless steel mixer with a steam heated jacket at a temperature of 125°C for 15 minutes, for sterilization purposes;
 - b) cooling the solution till it reaches a temperature between 5 and 30°C;
 - c) adding 0.5 to 5% of ethanol and 2 to 50% of an inoculum of *Acetobacter xylinum*, followed by agitation of the solution until it is homogenized;
 - d) transferring the solution to covered fermentation trays where it must rest for 16 to 240 hours, at a temperature between 5 and 30°C;
 - e) collecting the cellulose wet sheets that are thus formed, varying from 0.25 to 200 mm in thickness; and
 - f) forwarding the wet sheets to the whirlpool tank, where they are purified and whitened, according to the following sequence: rinsing, washing with sodium hydroxide 1 to 5%, rinsing, washing with 1 to 5% sodium lauryl sulfate and final rinsing;
- wherein the cellulosic wet sheet is permeable to gases and impermeable to liquids.

2. (Currently amended) The A process for obtaining a cellulosic membrane of claim 1, further comprising:

a) heating a solution containing 0.2 to 12% of glucose mass and 0.1 to 7% of yeast extract in water that was filtered through sand and activated charcoal in a sanitary stainless steel mixer with a steam heated jacket at a temperature of 125°C for 15 minutes, for sterilization purposes;

b) cooling the solution till it reaches a temperature between 5 and 30°C;

c) adding 0.5 to 5% of ethanol and 2 to 50% of an inoculum of Acetobacter xylinum, followed by agitation of the solution until it is homogenized;

d) transferring the solution to covered fermentation trays and allowing the solution to rest for 16 to 240 hours, at a temperature between 5 and 30°C;

e) collecting cellulose wet sheets that are thus formed, varying from 0.25 to 200 mm in thickness; and

f) forwarding the cellulose wet sheets to a whirlpool tank where they are purified and whitened according to the following sequence: rinsing, washing with sodium hydroxide 1 to 5%, rinsing, washing with 1 to 5% sodium lauryl sulfate and final rinsing; wherein the cellulosic wet sheet is permeable to gases and impermeable to liquids;

g) in one extremity of the wet sheet, applying two rectangles of an absorbent material by pressure, a first of the two rectangles of absorbent material applied to a first side of the wet sheet and a second of the two rectangles of absorbent material applied to a second side of the wet sheet so as to obtain a semi-rigid end that will not adhere to the drying material;

h) inserting the extremity in drying equipment through an idling roller and introducing the extremity between two pairs of draining cylinders, and from there to a pair of conveyor belts, pressing the wet sheet between these belts with

increasing force (from 0.5 to 8 kgf/cm²) applied by a series of spaced apart small rollers heated by hot water that circulates in the small roller axles; and passing the wet sheet to a pair of finishing cylinders, which may or may not be heated to create a smooth surface for the membrane;

i) forwarding the membrane formed by the drying of the wet sheet to a coiling device where the product is coiled.

3. (Withdrawn) Process used to obtain cellulosic wet sheet according to claim 1, characterized by optionally comprising a step where screens or other artifacts of diverse materials are added to the surface of the wet sheet already pre-formed; then this set rests for another period of time that may vary from 16 to 240 hours at a temperature between 5 and 30.degree. C. followed by the collecting of the compound cellulose wet sheets thus formed varying from 0.25 to 40 mm in thickness;

4. (Withdrawn) "Culture medium" used in the process in claim 1, characterized by containing water filtered; 0.2 to 12% of glucose mass; 0.1 to 7% of yeast extract, and 0.5 to 5% of ethanol.

5. (Withdrawn) "Fermentation tray" used in the process in claim 1, characterized by its consisting of a tray (11) with a double wall (12) and a covering (13); made of non-adherent material, preferably fiberglass with a reinforced structure. Said tray walls are 2 to 3 mm thick and form a duct where water circulates in order to keep the temperature at the ideal point for fermentation.

6. (Withdrawn) Fermentation tray according to claim 5, characterized by the fact that the tray covering (13) is made of the same material of the tray (11) and is

embedded in the set, said tray covering consists of modules bonded together by rubber, preferably nitrile, thus allowing the liquid medium to be loaded into the tray by raising only the first and smaller module, reducing the exposure of the medium to contamination.

7. (Withdrawn) Equipment used to obtain the membrane, according to the process in claim 2, characterized by its consisting of: a black steel plate (1) structure of appropriate thickness, forming a box with a lid (2) that is normally closed and, for the purpose of ensuring the operator's safety, is provided with a power switch that arrests the motor when the lid is not totally shut, and an idling roller (3) coated with an absorbent material. two pairs (4 and 4') of draining cylinders made of stainless steel coated with an absorbent material, 20 cm in diameter and 30 cm in width, where the upper cylinder (4) of the first pair is provided with a foot-actuated lifting mechanism (5) and a lever system designed to permit the initial positioning of the wet sheet between the two cylinders; two pairs (6 and 6') of stainless steel driving cylinders, 20 cm in diameter and 30 cm in width, with roller bearings, where the cylinders numbered (6) are not powered and the cylinders numbered (6') are powered with a speed varying from 15 to 60 RPM; two felt (or any other water absorbing material) continuous conveyor belts measuring 2 m by 30 cm that are moved by the cylinders (6'); as well as two rollers (7) to control the tension on the belts, also made of stainless steel, with 10 cm in diameter; twelve or more pairs of stainless steel rollers (8, 8'), their external diameters measuring 5 cm each, the bottom ones (8') heated by the passing of hot water or vapor through their axles; each pair of rollers (8, 8') makes it possible to apply increasing pressure to the conveyor belts made of absorbent material; a pair of finishing cylinders (9) made of polished stainless steel, 20 cm in diameter and 30 cm long, each exerting pressure

on the other, that can be heated by inner circulation of steam or hot water; and a coiling device (10) made of carbon steel.

8. (Withdrawn) "Cellulosic membrane" characterized for being inert, biocompatible and composed of pure cellulose microfibrils produced by microorganisms, randomly arranged, with an ideal weigh somewhere between 10 and 45 g/m², being said membrane permeable to gases and impermeable to liquids.

9. (Withdrawn) "Process used to obtain a wet sheet" in accordance with claim 1, characterized by the fact that all effluents are recovered and treated before they are reused or disposed of in the sewer system.

10. (Withdrawn) "Process used to obtain a wet sheet" in accordance with claim 1, characterized by the fact that the wet sheet obtained is made of randomly arranged pure cellulose microfibrils with a great capacity to retain liquids, keeping the humidity retained in its structure in excess of 90%, and that said wet sheet is cartilage-like and of a whitish color.

11. (Withdrawn) Process used to obtain a wet sheet in accordance with claim 1, characterized by the fact that the sheets obtained resist high temperatures and optionally may be submitted to autoclave treatment in liquid medium under high temperature and pressure without suffering any physical changes;

12. (Withdrawn) Process used to obtain a wet sheet in accordance with claim 1, characterized by the fact that the sheets obtained are insoluble in organic

solvents, and that they may be processed in blenders, mills or the equivalent, resulting in a thick mass with a great power to retain liquids.

13. (Withdrawn) Process used to obtain a wet sheet in accordance with claim 1, characterized by the fact that the sheets obtained are used as thickening and/or stabilizer in the food and beverage industry.

14. (Withdrawn) Process used to obtain a wet sheet in accordance with claim 1, characterized by the fact that the sheets obtained in the form of a thick mass can be used also in the production of lightweight plates extremely resistant to impact and bullet perforations.

15. (Withdrawn) Process used to obtain a wet sheet in accordance with claim 14, characterized by the fact that said plates are obtained by grinding the wet sheet in a liquid medium, then dehydrating the mass of cellulose microfibrils in such a way as to recast the material to form a plate to be molded as desired as to form and thickness.

16. (Withdrawn) Process used to obtain a wet sheet in accordance with claim 1, characterized by the fact that the sheets obtained are used as thickeners or stabilizers in nonfat milk, juices and food in general; used in the making of artifacts obtained by drying and shaping the wet sheets (compound and not compound alike) in the forms desired for the final product, either pressed or non-pressed; included in the composition of canned foods; used in the production of sweets; and used to obtain extremely thin cellulosic membranes with characteristic properties such as permeability to gases and impermeability to liquids.

17. (Withdrawn) Process used to obtain a wet sheet in accordance with claim 1. characterized by the fact that the sheets obtained, submitted to a fast vacuum drying process or to lyophilization, are transformed in a super absorbent and biocompatible material, a hemostatic both of internal and external use in hospital and surgical applications.

18. (Previously presented) The process of claim 2, wherein said membrane is composed of pure cellulose microfibrils produced by microorganisms, randomly arranged, with an ideal weight somewhere between 10 and 45 g/m².

19. (Previously presented) The process of claim 2, wherein said membrane is inert and biocompatible, so as not to cause allergic or rejection responses when applied over wounds in live organisms.

20. (Canceled)

21. (Currently amended) The process of claim 2, wherein the membrane obtained are is used as a device to obtain an environment suitable for "in vivo" culture in the regeneration of tissues in living organisms, both externally and internally, due to their biocompatibility that prevents rejection; as a temporary substitute for the skin, mainly in dermal ulcers, burns, recovery of autograft-donor sites, for ophthalmic use, odontological use, dressings for home use, professional use, veterinary use; as functional material in the making of hospital attire and disposable packaging for medical and nursing instruments whenever a microbial barrier is recommended, and also as thickener to replace sugar, starch,

Applicant: Levy et al.
Application No.: 10/538,131

carboxymethylcellulose, and microcrystalline cellulose in the making of medicine tablets; as engineering and safety material, specially as a bulletproof material; and as diaphragm in the production of speakers and earphones.